280 Natural

REINFORCED WATER-ACTIVATED TAPE

TECHNICAL DATA SHEET

DESCRIPTION

3-way fiberglass reinforced natural kraft carton sealing tape manufactured with wateractivated adhesive.

PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons and non-unitized loads. Recommend using on heavyweight cartons up to 90 pounds (41 kg).

PHYSICAL PROPERTIES:

 Caliper
 7.9 mils (0.20mm)

 MD Tensile
 96 lb/in (420 N/25mm)

 CD Tensile
 29 lb/in (127 N/25mm)

ADHESION (WATER AT RECOMMENDED 110°F/43°):

Fipago:

 2/0
 37

 2/1
 57

 5/0
 68

 15/0
 86

McLaurin: 85

intertape polymer group

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

CONSTRUCTION PER 3.000 SOUARE FEET (metric)

Top Ply: 30 lb (49 g/m²)

INTERTAPE POLYMER GROUP®

Natural Kraft Paper

(virgin fibers)

Bottom Ply: 30 lb (49 g/m²)

Natural Kraft Paper

(virgin fibers)

Laminating Adhesive: High Melt Index

Polypropylene Based

Co-Polymer

Water-Activated Adhesive: Chemically Grafted Starch

Based Copolymer Adhesive,

Designated as S3911

MD Reinforcement (3-3-2-2-3-3) 75 Fiberglass

(per 3"), 1/2" spacing

CD Reinforcement (1-1-1) 150 Fiberglass,

0.55" spacing, 43° angle





EFFECTIVE: 03/16